AMENDMENTS TO THE SPECIFICATION

Page 17, delete Table 2 at lines 6-7 and replace with the following new Table 2.

Table 2

No.	Outer Diameter (mm)	Height (mm)	Inner Diameter (mm)	Mechanical Resonance Frequency f ₀ (kHz)	Impedance Distortion- Generating Frequency (kHz)
A1	3.0	3.0	1.0	<u>916</u> 863	793
A2	3.5	3.0	1.0	<u>814</u> 767	772
A3	4.0	3.0	1.0	<u>733</u> 690	706
A4	3.5	1.5	1.0	<u>814</u> 767	864
A5	3.5	3.5	1.0	<u>814</u> 767	724
A6	3.5	4.0	1.0	<u>814</u> 767	628
A7	3.5	4.5	1.0	<u>814</u> 767	598

Page 17, delete the last full paragraph bridging pages 17-18 and insert the following paragraph:

As the outer diameter of the ferrite core increases, the impedance distortion-generating frequency decreases, resulting in good accordance with the calculation results of the mechanical resonance frequency f_0 . Though the mechanical resonance frequency f_0 is determined without taking into account the thickness of the toroidal core, it has been found that the thicker the ferrite core, the smaller the impedance distortion-generating frequency. In this case, too, impedance distortion occurs in a range of $f_0 \pm 200 \text{ kHz}$. It has been confirmed from these results that the

AMENDMENT/RESPONSE TO RESTRICTION REQUIREMENT U.S. Appln. No. 10/649,777

impedance distortion is caused by the magnetostriction vibration phenomenon of the ferrite core.